


REC'D 15 AUG 2001

WIPO

PCT

## INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference 002854wo Me/tg		<b>FOR FURTHER ACTION</b>	See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)
International application No. PCT/US99/09945	International filing date (day/month/year) 05/05/1999	Priority date (day/month/year) [05/05/1999]	
International Patent Classification (IPC) or national classification and IPC C09J183/07			
Applicant 3M INNOVATIVE PROPERTIES COMPANY et al.			
<p>1. This international preliminary examination report has been prepared by this International Preliminary Examining Authority and is transmitted to the applicant according to Article 36.</p> <p>2. This REPORT consists of a total of 6 sheets, including this cover sheet.</p> <p><input checked="" type="checkbox"/> This report is also accompanied by ANNEXES, i.e. sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications made before this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions under the PCT).</p> <p>These annexes consist of a total of 1 sheets.</p>			
<p>3. This report contains indications relating to the following items:</p> <ul style="list-style-type: none"> <li>I <input checked="" type="checkbox"/> Basis of the report</li> <li>II <input type="checkbox"/> Priority</li> <li>III <input type="checkbox"/> Non-establishment of opinion with regard to novelty, inventive step and industrial applicability</li> <li>IV <input type="checkbox"/> Lack of unity of invention</li> <li>V <input checked="" type="checkbox"/> Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement</li> <li>VI <input type="checkbox"/> Certain documents cited</li> <li>VII <input type="checkbox"/> Certain defects in the international application</li> <li>VIII <input checked="" type="checkbox"/> Certain observations on the international application</li> </ul>			
Date of submission of the demand  17/11/2000		Date of completion of this report  13.08.2001	
Name and mailing address of the international preliminary examining authority:  European Patent Office D-80298 Munich Tel. +49 89 2399 - 0 Tx: 523656 epmu d Fax: +49 89 2399 - 4465		Authorized officer  Lartigue, M-L  Telephone No. +49 89 2399 8230	



**INTERNATIONAL PRELIMINARY  
EXAMINATION REPORT**

International application No. PCT/US99/09945

**I. Basis of the report**

1. With regard to the **elements** of the international application (*Replacement sheets which have been furnished to the receiving Office in response to an invitation under Article 14 are referred to in this report as "originally filed" and are not annexed to this report since they do not contain amendments (Rules 70.16 and 70.17)*):

**Description, pages:**

1,3-40 as originally filed

2 as received on 16/07/2001 with letter of 13/07/2001

**Claims, No.:**

1-34 as originally filed

2. With regard to the **language**, all the elements marked above were available or furnished to this Authority in the language in which the international application was filed, unless otherwise indicated under this item.

These elements were available or furnished to this Authority in the following language: , which is:

- ☐ the language of a translation furnished for the purposes of the international search (under Rule 23.1(b)).
- ☐ the language of publication of the international application (under Rule 48.3(b)).
- ☐ the language of a translation furnished for the purposes of international preliminary examination (under Rule 55.2 and/or 55.3).

3. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application, the international preliminary examination was carried out on the basis of the sequence listing:

- ☐ contained in the international application in written form.
- ☐ filed together with the international application in computer readable form.
- ☐ furnished subsequently to this Authority in written form.
- ☐ furnished subsequently to this Authority in computer readable form.
- ☐ The statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.
- ☐ The statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished.

4. The amendments have resulted in the cancellation of:

- ☐ the description, pages:
- ☐ the claims, Nos.:
- ☐ the drawings, sheets:

**INTERNATIONAL PRELIMINARY  
EXAMINATION REPORT**

International application No. PCT/US99/09945

5. ☐ This report has been established as if (some of) the amendments had not been made, since they have been considered to go beyond the disclosure as filed (Rule 70.2(c)):

*(Any replacement sheet containing such amendments must be referred to under item 1 and annexed to this report.)*

6. Additional observations, if necessary:

**V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement**

1. Statement

Novelty (N)	Yes: Claims 1-34
	No: Claims
Inventive step (IS)	Yes: Claims
	No: Claims 1-34
Industrial applicability (IA)	Yes: Claims 1-34
	No: Claims

2. Citations and explanations  
**see separate sheet**

**VIII. Certain observations on the international application**

The following observations on the clarity of the claims, description, and drawings or on the question whether the claims are fully supported by the description, are made:  
**see separate sheet**

**Re Item V**

**Reasoned statement under Article 35(2) with regard to novelty and inventive step;  
citations and explanations supporting such statement**

1. Reference is made to the following documents:

**D1: EP 0 581 539 A**

**D2: US 5 721 136 A**

**D3: US 5 082 706 A**

2. NOVELTY (Art. 33(2) PCT) and INVENTIVE STEP (Art. 33(3) PCT): the subject-matter of present claims 1 to 34 is novel but does not involve an inventive step.

2.1. D1 discloses a composition to provide pressure sensitive adhesives comprising (see D1, claims 1, 2, 3 and 4):

- (A) an organopolysiloxane MQ resin which contains  $(R)_3SiO_{1/2}$  and  $SiO_2$  units in a molar ratio in the range of 0,6 to 0,9, R being a monovalent hydrocarbon radical having from 1 to 6 carbon atoms. Said MQ resin also contains hydroxyl radicals and at least in the embodiment of D1, claim 2, more than 95% of all R groups are methyl groups;

- (B) an organohydrogenpolysiloxane free of aliphatic insaturation in a quantity sufficient to provide from 1,1 to 15 silicon bonded hydrogen atoms per alkenyl group (see D1, claim 1 page 13, line 1);

- (C)(i) an alkenyl-terminated organopolysiloxane having the general formula  $R^2R^3_2SiO(R^3_2SiO)_zSiR^3_2R^2$  where  $R^2$  is an alkenyl group such as vinyl,  $R^3$  is an alkyl group and z is from 1 to 300;

- (C)(ii) a polydiorganosiloxane having the formula  $R^2R^3_2SiO(R^3_2SiO)_m(R^2R^3SiO)_nR^3_2R^2$  where  $R^2$  and  $R^3$  are as defined above;

- (E) a hydrosilation catalyst in a amount sufficient to provide at least 0,1 part by weight platinum for one million parts by weight of the combined weight of (A), (B) and (C) (see D1, page 6, line 52).

Moreover, D1, claim 9 discloses a method of making an adhesive comprising:

- (i) applying the above cited composition to at least one surface of a support and
- (ii) heating said composition to cure it.

D1 also discloses articles such as pressure sensitive adhesive tapes (see D1, page

9, line 10), as defined in present claims 10 and 17.

In D1, claim 1 when z is 300, the molecular weight of (C)(i) is greater than 20 000 but the molecular weight of (C)(ii) is not specified.

Since the combination of a polydiorganosiloxane having an average molecular weight of at least 20 000 with a polydiorganosiloxane having an average molecular weight of less than 20 000 is not explicitly disclosed in D1, the subject-matter of present independent claim 1 is novel.

The subject-matter of present claim 1 being novel, the subject-matter of present claims 2 to 34 is also novel.

The problem to be solved by the present application may be regarded as to provide a further adhesive composition having a good peel adhesive strength.

The adhesive composition proposed in present claim 1 does not involve an inventive step for the following reasons:

- in D1, claim 1 when z is 300 the molecular weight of (C)(i) is greater than 20 000;
- in D1 Examples 3-7 and 19, the molecular weight of (C)(ii) calculated from the vinyl equivalent weight and the number of vinyl groups is less than 20 000;
- it is part of the routine activity of the skilled person to investigate various average molecular weights of the two polydiorganosiloxanes with a view to optimize the properties of the composition.

Since the adhesive composition of present claim 1 lacks inventive step, the subject-matter of present claims 10 and 33 also lacks inventive step.

- 2.2. D2 is considered to represent the closest prior art for the subject-matter of present claim 18, because it discloses an analytical receptacle comprising a surface and a cover tape adhered to the surface, wherein the cover tape comprises a backing and a sealing layer in contact with the receptacle surface (see D2, Fig. 2-3 and claim 1). Said sealing layer may be made from compositions of silicone, cured or uncured (see D2, column 4, lines 59-60). The surface adhesiveness may be adjusted by varying the composition of the sealing layer (see D2, column 5, lines 14-19). In addition, the cover tape according to D2 may have a removable release liner to protect the sealing layer, i.e. the adhesive part of the cover tape (see D2, column 4, line 39-41).

D2, indicates the use of a cured silicone as a sealing layer in the cover tape

of the analytical receptacle. To use an adhesive as defined in present claim 1, which does not involve an inventive step, as a sealing layer in the analytical receptacle of D2 cannot establish an inventive step.

Therefore, the subject-matter of present claim 18 lacks inventive step.

- 2.3. The adhesive compositions disclosed in D1 and D3 (see D3, claim 1) comprise all the components of the adhesive used in the analytical receptacle as defined in present claims 31 and 32. Hence, the subject-matter of said claims 31 and 32 does not involve an inventive step for the same reasons as set out in paragraph 2.2. above.
- 2.4. Dependent claims 2-9, 11-17, 19-30 and 34 do not contain any features which, in combination with the features of claims 1, 10, 18 and 33 to which they refer, meet the requirements of the PCT in respect of inventive step, because it is not apparent from the present description what problem is solved by the distinguishing features vis-à-vis D1 and D2.

#### **Re Item VIII**

##### **Certain observations on the international application**

1. The word "about" in connection with ranges e.g. in claims 1, 4-7, 13-15, 22-24 and 32 and in the description renders the scope of the claims unclear (Art. 6 PCT).
2. The "incorporation by reference" of the entire contents of other documents could lead to doubt as to the extent of protection sought by the claims (see description page 40, lines 10-11).
3. The attention of the applicant is drawn to the fact that the present application lacks unity (Rule 13 PCT) because it relates to a group of inventions which are not linked to form a single general inventive concept. As a matter of fact, the adhesive composition as defined in present independent claim 1 differs from the adhesive composition as defined in present independent claims 31 and 32.

56

## PCT

## INTERNATIONAL SEARCH REPORT

(PCT Article 18 and Rules 43 and 44)

Applicant's or agent's file reference <b>54846PCT6A</b>	<b>FOR FURTHER ACTION</b> see Notification of Transmittal of International Search Report (Form PCT/ISA/220) as well as, where applicable, item 5 below.	
International application No. <b>PCT/US 99/ 09945</b>	International filing date (day/month/year) <b>05/05/1999</b>	(Earliest) Priority Date (day/month/year)
Applicant <b>3M INNOVATIVE PROPERTIES COMPANY et al.</b>		

This International Search Report has been prepared by this International Searching Authority and is transmitted to the applicant according to Article 18. A copy is being transmitted to the International Bureau.

This International Search Report consists of a total of 3 sheets.

☒ It is also accompanied by a copy of each prior art document cited in this report.

## 1. Basis of the report

- a. With regard to the **language**, the international search was carried out on the basis of the international application in the language in which it was filed, unless otherwise indicated under this item.

☐ the international search was carried out on the basis of a translation of the international application furnished to this Authority (Rule 23.1(b)).

- b. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application, the international search was carried out on the basis of the sequence listing :

☐ contained in the international application in written form.

☐ filed together with the international application in computer readable form.

☐ furnished subsequently to this Authority in written form.

☐ furnished subsequently to this Authority in computer readable form.

☐ the statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.

☐ the statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished

2. ☐ **Certain claims were found unsearchable** (See Box I).

3. ☐ **Unity of invention is lacking** (see Box II).

4. With regard to the **title**,

☒ the text is approved as submitted by the applicant.

☐ the text has been established by this Authority to read as follows:

5. With regard to the **abstract**,

☒ the text is approved as submitted by the applicant.

☐ the text has been established, according to Rule 38.2(b), by this Authority as it appears in Box III. The applicant may, within one month from the date of mailing of this international search report, submit comments to this Authority.

6. The figure of the **drawings** to be published with the abstract is Figure No.

☐ as suggested by the applicant.

☐ because the applicant failed to suggest a figure.

☐ because this figure better characterizes the invention.

☒ None of the figures.

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09J183/07 B65B9/04

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09J B65B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 581 539 A (GEN ELECTRIC) 2 February 1994 (1994-02-02) claims 1,3,4,9 page 5, line 31 -page 6, line 9 ---	1-3
A	US 5 082 706 A (TANGNEY THOMAS J) 21 January 1992 (1992-01-21) cited in the application claim 1 ---	1
A	US 5 721 136 A (TITCOMB PAUL ET AL) 24 February 1998 (1998-02-24) cited in the application claims 1-14 --- -/--	1

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## ° Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&amp;" document member of the same patent family

Date of the actual completion of the international search

5 January 2000

Date of mailing of the international search report

18/01/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Depijper, R



## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 729 963 A (BIRD GERALD C) 24 March 1998 (1998-03-24) cited in the application claim 1	1
A	EP 0 506 372 A (GEN ELECTRIC) 30 September 1992 (1992-09-30) claim 1	1

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/09945

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
EP 0581539	A	02-02-1994	CA	2101708 A		31-01-1994
			JP	6166861 A		14-06-1994
<hr/>						
US 5082706	A	21-01-1992	AT	86286 T		15-03-1993
			CA	2002073 A		23-05-1990
			EP	0370689 A		30-05-1990
			IE	62700 B		22-02-1995
			JP	2189383 A		25-07-1990
			KR	141486 B		15-06-1998
<hr/>						
US 5721136	A	24-02-1998	NONE			
<hr/>						
US 5729963	A	24-03-1998	US	5648136 A		15-07-1997
			CN	1190524 A		12-08-1998
			DE	69601802 D		22-04-1999
			DE	69601802 T		04-11-1999
			EP	0838137 A		29-04-1998
			JP	11509163 T		17-08-1999
			WO	9703545 A		30-01-1997
<hr/>						
EP 0506372	A	30-09-1992	US	5466532 A		14-11-1995
			CA	2061973 A		27-09-1992
			DE	69206457 D		18-01-1996
			DE	69206457 T		11-07-1996
			JP	5098240 A		20-04-1993

## SILICONE ADHESIVES, ARTICLES, AND METHODS

5

### Field of the Invention

The invention relates to silicone adhesives, articles, and methods of making and using. The adhesives are particularly useful on articles such as cover tapes for analytical receptacles, such as microtiter plates, microfluidic  
10 devices, discrete or continuous multi-reservoir carriers, or other analytical receptacles, particularly those that are designed for holding a variety of liquids, in bioanalytical applications, for example.

### Background

15 Microtiter plates are well known for use in handling liquid materials in bioanalytical assays for multiple, rapid, low-volume analysis. A typical screening technique combines an assay plate, having multiple depressions or wells, with liquid handling hardware to provide a rapid, automated system of analysis. In a current, standard analytical system, each  
20 assay plate accommodates 96 wells, each well being addressable by suitably programmed hardware. The capacity of each of the 96 wells is about 0.2 milliliter (ml) to about 0.4 ml. Smaller capacity wells lead to assay plates that accommodate a larger number of samples. For example, assay plates containing 1536 wells, each with a capacity of less than 5 microliters ( $\mu$ l) are known.  
25 These plates, with increased sampling capability, have demonstrated usefulness in a variety of assays, including enzyme assays, receptor-ligand assays, and even cell based assays. The increased number of sample wells, per assay plate, demands increased precision of the hardware associated with analysis using these assay plates.

30 Liquid handling for bioanalytical applications, using assay plates of either the 96-well, 384-well, or the 1536-well variety, may be viewed as a

batch process with rate limitation due to the loading and positioning of the assay tray. Possible improvement in the rate of sample analysis results from the use of a continuous strip of material having sample wells molded along its length. U.S. Pat. No. 4,883,642 (Bisconte) suggests such a strip or tape. The patent teaches a  
5 continuous ribbon, which may be either smooth or suitably molded to incorporate a plurality of micro-wells. Fixed biological sample analysis uses smooth versions of the continuous ribbons while micro-well ribbons find use for analyzing living biological samples. Two tracks, positioned along opposite edges of the ribbon, provide addressable means for moving and positioning the  
10 ribbon in a selected, precise location with adjustment accurate to 10 micrometers ( $\mu\text{m}$ ). The tracks may be coded using magnetic, optical, or computer methods, for example, which allow manipulation and positioning of the ribbon. A dosage syringe type of device, positioned using a step by step motor, distributes biological samples in the micro-wells.

15 This continuous multi-reservoir carrier is useful in the automated analysis of biological samples, such as histological sections. Protection of the samples, whether applied to a smooth ribbon or contained in micro-wells may use a self-adhesive film. The self-adhesive film covers the smooth film surface or seals the openings to the individual micro-wells. It may be permeable or  
20 impermeable to air.

U.S. Pat. No. 5,721,136 (Finney et al.) teaches the use of a multilayer sheet having a silicone adhesive thereon for use on vessels for biochemical reactions. One layer provides strength and integrity for the film. The second layer is a thick, in the range of about 2 mils to about 40 mils (50  $\mu\text{m}$   
25 to 1016  $\mu\text{m}$ ), deformable material with a very low tack surface. The elastic nature of the second layer results in good seal when clamped down during thermal cycling. The rubbery materials also provide a very low level of adhesion. The peel force of the sheet from a polypropylene surface is reported to be in the range of 0.11 N/dm to 0.5 N/dm (0.1 oz/in to 4.5 oz/in). Although a

low tack adhesive tape is desirable to prevent the tape from sticking to rubber gloves commonly used in biological research, when applied to a microplate, for example, low adhesion of thick, elastic adhesive tapes is likely to cause a high evaporation rate and increase the incidence of cross-contamination during

5 storage and handling.

To increase cohesive strength and reduce contamination due to residual adhesive, silicone may be cured or crosslinked by catalysts such as peroxide or metallic salts at elevated temperatures. For example, benzoyl peroxide requires a cure temperature of more than 150°C for the catalyst to be  
10 functional. Consequently, a backing with low melting or softening point, such as a polyethylene film, may be overly stretched or distorted dimensionally during curing. To prepare a curable silicone tape, one common practice is to coat curable silicones on a release liner consisting of a fluorosilicone coating and PET (polyethylene terephthalate) backing. The tape is then laminated with the  
15 backings of low melting or softening point temperatures. Since release liners are commonly used to process and to protect silicone adhesive surfaces, it is important that the release force to separate the tape from the release liner be kept at a low level to minimize distortion of the tape backing, particularly when the release liner is removed during an automatic process.

20 U.S. Pat. No. 5,082,706 (Tangney) describes a silicone PSA/fluorosilicone release laminate having a release force of less than 7.7 N/dm (7 oz/in) from the fluorosilicone release layer and a peel adhesion of at least 46.4 N/dm (42.2 oz/in). This adhesive includes a tackifying resin (often referred to as an MQ resin) containing two structural units, one of which is  $R_3SiO_{1/2}$   
25 (often designated as M) and the other  $SiO_{4/2}$  (often designated as Q). As discussed in The Handbook of Pressure-Adhesive Technology, 2<sup>nd</sup> Edition, (ed. D. Satas, 1989) p. 510, the peel adhesion of silicone pressure sensitive adhesives can be controlled by controlling the amount of tackifying resin. For example, increasing the amount of tackifying resin increases the peel adhesion; however,

there is typically a point at which the peel adhesion maximizes. Thus, increasing the amount of tackifying resin beyond this point can cause peel adhesion to decrease.

5

### Summary of the Invention

What is needed are adhesives and adhesive articles, particularly cover tapes for analytical receptacles, that provide an effective peel strength from the materials that typically form analytical receptacles yet good release  
10 from a release liner and preferably sufficiently low tack as to be suitable for use with analytical receptacles. Such adhesives would be especially desirable if they are substantially resistant to liquids, particularly organic solvents such as dimethyl sulfoxide that are often used in bioanalytical applications.

The present invention provides adhesives, preferably pressure  
15 sensitive adhesives (PSAs), adhesive articles, and methods. Preferably, the articles are cover tapes for analytical receptacles, such as microtiter plates, microfluidic devices, and continuous multi-reservoir carriers, or other analytical receptacles or biosensors, for example. Typically, such analytical receptacles are used in bioanalytical applications and are designed for containing solids and  
20 fluids, including liquids, gases, powders, and gels, which may include biological samples or organic solvents, for example.

In preferred embodiments, cover tapes for such analytical receptacles provide a sealing membrane so that each reservoir, such as a well or channel, for example, is part of a sealed enclosure to retain the contents and/or  
25 reduce evaporation and contamination of the contents of the receptacle. Preferred cover tapes have sufficient transparency to allow for photometric analysis and/or visual inspection and are substantially resistant to solvents commonly used in bioanalytical applications, such as dimethyl sulfoxide (DMSO), water, acetonitrile/water, methanol, ethanol, or mixtures thereof, for

example. As used herein, a substantially solvent-resistant cover tape, and particularly adhesive, is one that does not substantially swell or dissolve in the solvent used in the particular application and does maintain sufficient adhesion to the analytical receptacle.

- 5 In one embodiment, the present invention provides a silicone adhesive, preferably, a pressure sensitive adhesive, which is prepared from components including: (a) a polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  and a number average molecular weight of at least 20,000, wherein each R is independently a monovalent hydrocarbon group, each
- 10  $R^1$  is independently an alkenyl group, and n is an integer; (b) a polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_m(R^1RSiO)_nSiR_2R^1$  and a number average molecular weight of less than 20,000, wherein each R and  $R^1$  is independently a monovalent hydrocarbon group, at least two  $R^1$  groups are alkenyl groups, and m and n are
- 15 integers the sum of which provide an alkenyl equivalent weight of about 250 to about 10,000; (c) an organopolysiloxane MQ resin which contains  $(R^2)_3SiO_{1/2}$  units and  $SiO_2$  units in a molar ratio in the range of 0.6:1 to 1:1, wherein each  $R^2$  is independently selected from the group of alkyl groups, alkenyl groups, or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl
- 20 groups; (d) an organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in components (a) through (c); and (e) a Group VIIIB-containing catalyst in a quantity sufficient to provide 0.1 to 1,000 weight parts Group VIIIB
- 25 metal for each one million weight parts of the combined quantity of components (a) through (d). Methods of making and methods of using such adhesives are also provided.

In another embodiment, the present invention provides an adhesive article that includes a substrate having disposed on at least one major

surface a silicone-based adhesive, preferably a pressure sensitive adhesive, of the above formula. Adhesive articles include tapes, labels, and other sheeting useful in various formats including medical, graphics, and analytical applications.

In yet another embodiment, the present invention provides an  
5 analytical receptacle that includes a surface, preferably having at least one reservoir therein, and a cover tape adhered to the surface; wherein the cover tape includes a backing and an adhesive of the formula above disposed on at least one major surface of the backing and in contact with the receptacle surface.

In still another embodiment, the present invention provides an  
10 analytical receptacle that includes a surface comprising polypropylene, polystyrene, or combination thereof, and a cover tape adhered to the surface; wherein the cover tape includes a backing and an adhesive disposed on at least one major surface of the backing and in contact with the receptacle surface, wherein the adhesive is prepared from components including: (a) a  
15 polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  wherein each R is independently a monovalent hydrocarbon group, each  $R^1$  is independently an alkenyl group and n is an integer; (b) an organopolysiloxane MQ resin which contains  $(R^2)_3SiO_{1.2}$  units and  $SiO_2$  units in a molar ratio in the range of 0.6:1 to 1:1, wherein each  $R^2$  is independently selected from the group  
20 of alkyl groups, alkenyl groups, or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl groups; (c) an organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in component (a) and  
25 component (b) if present; and (d) a Group VIIIB-containing catalyst in a quantity sufficient to provide 0.1 to 1,000 weight parts Group VIIIB metal for each one million weight parts of the combined quantity of components (a) through (c).



In yet another embodiment, the present invention provides an analytical receptacle that includes a surface and a cover tape adhered to the surface; wherein the cover tape includes a backing and an adhesive disposed on at least one major surface of the backing and in contact with the receptacle surface, wherein the adhesive is prepared from components including: (a) a polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  wherein each R is independently a monovalent hydrocarbon group, each  $R^1$  is independently an alkenyl group and n is an integer; (b) an organopolysiloxane MQ resin which contains  $(R^2)_3SiO_{1.2}$  units and  $SiO_2$  units in a molar ratio in the range of 0.6:1 to 1:1, wherein each  $R^2$  is independently selected from the group of alkyl groups, alkenyl groups, or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl groups; (c) an organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in component (a) and component (b) if present; and (d) a Group VIIB-containing catalyst in a quantity sufficient to provide 0.1 to 1,000 weight parts Group VIIB metal for each one million weight parts of the combined quantity of components (a) through (c); wherein the adhesive when disposed on a fluorosilicone-coated polyethylene terephthalate release liner and a propylene/ethylene copolymer backing at a coating weight of 0.8 grams/154.8 cm<sup>2</sup> to form a laminate, and when adhered to a glass plate, displays a 180° release force of no greater than about 20 N/dm when measured at 30.5 cm/minute and room temperature.

The analytical receptacle can be in the form of a substantially continuous tape or it can be in discrete shapes and sizes, preferably with one or more reservoirs. For example, the analytical receptacle can be in the form of a microtiter plate, a microfluidic device comprising a substrate and one or more channels therein, or a substantially continuous polymeric strip (i.e., tape) comprising a plurality of reservoirs at predetermined intervals (preferably,

uniformly spaced) along its length. Thus, the reservoir(s) can be in a wide variety of shapes and sizes. Preferably, they form wells or channels.

The adhesive of the present invention can form a pattern on the substrate (e.g., backing of a cover tape) or it can form a continuous layer on at least one major surface thereof. It is preferably a pressure sensitive adhesive, which unlike a heat activated adhesive, typically uses pressure to engage adhesion and does not require the use of a heating device. Certain preferred tapes of the present invention can also be conveniently repositioned to different locations or repositioned to the same location for resealing purposes if desired.

10

### **Detailed Description of Preferred Embodiments**

The present invention provides silicone-based adhesives, preferably, pressure sensitive adhesives, articles on which such adhesives are disposed (e.g., tapes), and methods of making and using such adhesives and articles. One particularly preferred article is a cover tape for an analytical receptacle. As used herein, analytical receptacles are devices that receive a sample, reagent, or solvent. Preferably, the device is configured to receive a volume of sample, reagent, or solvent, most preferably a microvolume. Such preferred configurations include one or more reservoirs. Examples include assay plate arrays (e.g., microtiter plates) and discrete or continuous (e.g., strip or tape) structures containing a plurality of wells, channels, or other reservoirs. Preferred analytical receptacles, without further modification, provide an open system of one or more reservoirs (e.g., wells or channels) to which fluids may be added directly. Open systems require careful control of evaporation and cross-contamination, which limits their practical applications. Thus, cover tapes are desirable as they result in closed systems that do not necessarily require specialized sample transport and containment.

25

A cover tape is applied along the length and width of an analytical receptacle to seal the receptacle, preferably the reservoir(s) of the

receptacle. Preferably, this results in producing individually sealed enclosures. Materials may be injected into or extracted from the closed reservoirs, through the cover tape, using suitable hypodermic-type needles, for example, if so desired. Preferred analytical receptacles can include one or more reservoirs.

- 5 They can be substantially continuous or discrete (i.e., noncontinuous) structures. For example, an analytical receptacle can be in the form of a microtiter plate that is conventionally used in bioanalytical methods. Alternatively, it can be a microfluidic device or continuous multi-reservoir carrier, for example, which can be cut into discrete (noncontinuous) pieces, if desired. Preferably,
- 10 conventional analytical receptacles are made of polyolefins, polystyrene, and/or polycarbonate, for example, and more preferably, polypropylene and/or polystyrene.

- A cover tape of the present invention, which acts as a sealing membrane, includes a silicone adhesive, preferably, a pressure sensitive silicone
- 15 adhesive, disposed on a backing. Preferably, the backing is made of a transparent material to allow for photometric analysis and/or visual inspection. A cover tape of the present invention preferably adheres well to materials of which conventional analytical receptacles are made (preferably polyolefins, polystyrene, polycarbonate, or combinations thereof, and more preferably,
- 20 polypropylene, polystyrene, or combinations thereof) and is preferably repositionable (i.e., the adhesive permits repeated cycles in which materials are alternatively bonded thereto and removed therefrom, while the adhesive is permanently retained on the backing of the adhesive article), but does not allow cross-contamination of sample materials in the individual reservoirs. Preferably,
- 25 the cover tape maintains adhesion during high and low temperature storage (e.g., about -80°C to about 200°C) while providing an effective seal against sample evaporation (e.g., less than 5% loss within 24 hours as used in a analytical quantitative analysis setting). Suitable cover tapes of the present invention allow for puncture by needles, such as stainless steel needles, or plastic sampling

pipette tips, for example, although cover tapes that resist puncture can also be used. These puncture sites may or may not reclose. The ability to be punctured and reclosed is typically controlled by the choice of backing material and/or thickness of the adhesive (e.g., a 0.01 cm thick adhesive layer may flow  
5 sufficiently to reclose a puncture site).

Because use of the cover tape can expose the adhesive to fluid contents of a reservoir, the choice of adhesive is of particular importance. Thus, it is important that the cover tape, and particularly the adhesive composition, does not substantially dissolve or otherwise react with solvents, such as dimethyl  
10 sulfoxide (DMSO) and acetonitrile/water, used commonly in bioanalytical research. Thus, preferred adhesives are substantially resistant to a wide variety of solvents, such as DMSO, water, acetonitrile/water, methanol, ethanol, or similar polar solvents, as well as mixtures thereof. That is, preferred adhesives do not substantially swell or dissolve in the solvent used in the particular  
15 application while they maintain sufficient adhesion to the analytical receptacle.

Furthermore, preferred adhesives are pressure-sensitive adhesives with sufficient cohesive strength that they leave little or no residue on the analytical receptacles or the needles or pipette tips after withdrawal from the puncture hole in the cover tape. This adhesive also preferably exhibits low tack,  
20 which serves to reduce adhesion of the cover tape to commonly used rubber gloves made from latex or nitrile rubber (e.g., no greater than about 10 N/dm peel force).

Preferred adhesives also are substantially biocompatible (i.e., substantially physiologically inert). As used herein, a "biocompatible" material  
25 is one that does not generally cause significant adverse reactions (e.g., toxic or antigenic responses) when in contact with biological fluids and/or tissues, such as tissue death, tumor formation, allergic reaction, inflammatory reaction, or blood clotting, for example.

The adhesives of the present invention include silicones, which

typically have excellent thermal and oxidative stability and a very broad service temperature range (i.e., a temperature range in which the adhesive is useful) of about -80°C to about 200°C. Silicone is also generally inert to a wide variety of polar chemicals and solvents, for example, water, methanol, ethanol,  
5 acetonitrile/water, and DMSO commonly used in bioanalytical testing. Furthermore, silicones are substantially biocompatible and are used in various medical devices. These properties make them excellent adhesives for use in, for example, cover tapes for analytical receptacles that are used in bioanalytical applications. However not all silicone adhesives in combination with all  
10 backings have the appropriate balance of properties (e.g., peel force, release force, and tack).

A silicone adhesive laminate disclosed in U.S. Pat. No. 5,082,706 (Tangney) includes an addition-cured silicone pressure sensitive adhesive on an addition-cured fluorosilicone release coating. When thin backings are employed  
15 in adhesive article constructions, it is desirable that upon separating the adhesive article (e.g., cover tape) from the release liner, release be sufficiently low that little if any permanent deformation of the backing occur. Thin backings (e.g., less than about 0.005 cm thick) and/or backings having low flexural modulus (e.g., polyolefins), deform easily. Thus, release forces required to separate  
20 adhesive articles based on such backings need to be very low to avoid inducing permanent deformation or curl in the adhesive article.

Although the release force needed to separate the adhesive from the fluorosilicone release coating of U.S. Pat. No. 5,082,706 (Tangney), after it is cast onto and cured in contact with the release coating, is reported to have a  
25 value of less than 200 grams per inch (7.7 N/dm), while at the same time displaying stable subsequent adhesiveness (46.4 N/dm from stainless steel) and stable subsequent tack, commercially available materials do not generally display sufficiently low release forces for many applications. For example, Dow Corning 7657 silicone adhesive displays a release force from a Rexam CLPET-

6J/000 transfer liner (fluorosilicone coating on a polyethylene terephthalate backing available from Rexam Release Corp., Bedford, IL) of 7.1 N/dm (see Example 1 for curing conditions). Although this is suitable for some applications, it is not typically suitable for transfer of the adhesive to very thin and/or fragile backings or in automated systems in which the release liner is removed. Thus, compositions providing lower release (e.g., no greater than about 5 N/dm) are particularly desirable for such applications.

The silicone adhesive of U.S. Pat. No. 5,082,706 is prepared from the following components: (a) a polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  wherein each R is independently a monovalent hydrocarbon group, each  $R^1$  is independently an alkenyl group and n is an integer; (b) an organopolysiloxane (often designated as an MQ resin) which contains  $(R^2)_3SiO_{1/2}$  units (often designated as M units) and  $SiO_2$  units (often designated as Q units) in a molar ratio in the range of 0.6:1 to 0.9:1, wherein each  $R^2$  is independently selected from the group of alkyl groups, alkenyl groups, or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl groups; (c) an organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in component (a) and component (b) if present; and (d) a platinum-containing catalyst in a quantity sufficient to provide 0.1 to 1,000 weight parts platinum for each one million weight parts of the combined quantity of components (a) through (c).

For certain embodiments of the present invention, similar and preferred adhesives can be used wherein: the hydrocarbon groups of the above formula can be alkyl and alkenyl groups, etc., up to, for example, groups containing 10 carbon atoms; the alkyl groups can be methyl, ethyl, propyl, hexyl, etc., up to, for example, groups containing 10 carbon atoms; the alkenyl groups can be vinyl, propenyl, hexenyl, etc., up to, for example, groups

containing 10 carbon atoms; the molar ratio of M to Q units in the MQ resin is in the range of 0.6:1 to 1:1; and a Group VIIB-containing metal catalyst.

Embodiments of the silicone adhesive of U.S. Pat. No. 5,082,706 that contain higher levels of the MQ resin typically display lower release values  
5 from the fluorosilicone liner, without significantly detrimentally affecting the peel values from other substrates (generally, polyolefins, polystyrene, polycarbonate, for example, and preferably, polypropylene and polystyrene).

Preferably, the level of MQ resin (and other components of the adhesives described herein) can be adjusted to provide an adhesive, which when  
10 disposed on a fluorosilicone-coated polyethylene terephthalate release liner and a ethylene/propylene copolymer backing at a coating weight of 0.8 grams/154.8 cm<sup>2</sup> to form a laminate, and when the laminate is adhered to a glass plate, displays a 180° release force of no greater than about 20 N/dm, more preferably, no greater than about 15 N/dm, even more preferably, no greater than about 10  
15 N/dm, and most preferably, no greater than about 5 N/dm, when measured at 30.5 cm/minute and room temperature (about 25°C to about 30°C). Preferably, the level of MQ resin (and other components of the adhesives described herein) can also be adjusted to provide an adhesive, which when disposed on a ethylene/propylene copolymer backing at a coating weight of 0.8 grams/154.8  
20 cm<sup>2</sup> and adhered to a polypropylene plate, displays a 180° peel force of at least about 5 N/dm, more preferably, at least about 10 N/dm, and most preferably, at least about 15 N/dm, when measured at 30.5 cm/minute and room temperature (about 25°C to about 30°C). Preferably, the peel force is no greater than about 50 N/dm.

25 Suitable types and amounts of the various adhesive components described above are those that are disclosed in U.S. Pat. No. 5,082,706 (Tangney). Typically, the amount of MQ resin (i.e., one in which R<sup>2</sup> is an alkyl group) needed to achieve desired levels of release and peel forces will depend on

the amount of the polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$ . Preferably, at least about 50 weight parts MQ resin and no greater than about 70 weight parts MQ resin is used to achieve the desired levels of peel and release forces, when the total weight parts (i.e., parts  
5 by weight) of MQ resin plus polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  equals 100 parts.

Alternatively to, or in addition to, increasing the level of MQ resin in the silicone adhesive of U.S. Pat. No. 5,082,706 to decrease the level of release force, a low molecular weight vinyl-substituted siloxane can be added to  
10 the composition. That is, the polydiorganosiloxane described above is actually present as a high molecular weight component and a low molecular weight component in these preferred embodiments of the adhesive. This low molecular weight component can be added as a component of a commercially available release modifier (e.g., Dow Corning SYL-OFF 7615 release modifier or General  
15 Electric Silicones SL-6030) typically used to increase release. Thus, the use of this material to decrease the release force is unexpected, particularly without significantly adversely affecting the peel force.

Such silicone pressure sensitive adhesives are prepared from the following components: (a) a polydiorganosiloxane having the general formula  
20  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  and a number average molecular weight of at least 20,000, wherein each R is independently a monovalent hydrocarbon group (such as alkyl groups, alkenyl groups, etc., up to, for example, groups containing 10 carbon atoms), each  $R^1$  is independently an alkenyl group (such as vinyl, propenyl, hexenyl, etc., up to, for example, groups containing 10 carbon atoms),  
25 and n is an integer; (b) a polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_m(R^1RSiO)_nSiR_2R^1$  and a number average molecular weight of less than 20,000, wherein each R and  $R^1$  is independently a monovalent hydrocarbon group (such as alkyl groups, alkenyl groups, etc. up to, for example, groups containing 10 carbon atoms), at least two  $R^1$  groups are alkenyl



groups (such as vinyl, propenyl, hexenyl, etc., up to, for example, groups containing 10 carbon atoms), and m and n are integers the sum of which provide an alkenyl equivalent weight of about 250 to about 10,000; (c) an organopolysiloxane (designated as an MQ resin) which contains  $(R^2)_3SiO_{1/2}$  units (designated as M units) and  $SiO_2$  units (designated as Q units) in a molar ratio in the range of 0.6:1 to 1:1, wherein  $R^2$  is selected from the group of alkyl (such as methyl, ethyl, propyl, hexyl, etc., up to, for example, groups containing 10 carbon atoms), alkenyl (such as vinyl, propenyl, hexenyl, etc., up to, for example, groups containing 10 carbon atoms), or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl groups; (d) an organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in components (a) through (c); and (e) a Group VIIIB-containing catalyst in a quantity sufficient to provide 0.1 to 1,000 weight parts Group VIIIB metal for each one million weight parts of the combined quantity of components (a) through (d). Preferably, such compositions include both nonfunctional and functional MQ resins, particularly alkenyl-functional MQ resins.

Suitable polydiorganosiloxanes having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  and a number average molecular weight of at least 20,000 are commercially available from sources such as Gelest Inc., Tullytown, PA. Examples are disclosed in U.S. Pat. No. 5,082,706 (Tangney). For particularly preferred embodiments, the molecular weight is preferably at least about 50,000, more preferably, at least about 100,000, and most preferably, at least about 250,000.

Suitable polydiorganosiloxane of the general formula  $R^1R_2SiO(R_2SiO)_m(R^1RSiO)_nSiR_2R^1$  and a number average molecular weight of less than 20,000 are commercially available from sources such as Gelest Inc. Preferred such materials have an alkenyl equivalent weight (as a result of the

choice of m and n) of about 250 to about 10,000, more preferably, about 250 to about 5000, and most preferably, about 250 to about 2000.

The high molecular weight polydiorganosiloxane component (i.e., having a number average molecular weight of at least 20,000) is preferably present in the adhesive compositions in an amount of at least about 50 weight parts and no greater than about 95 weight parts, and the low molecular weight polydiorganosiloxane component (i.e., having a number average molecular weight of less than 20,000) is preferably present in the adhesive compositions in an amount of at least about 5 weight parts and no greater than about 50 weight parts, based on the total parts by weight of both the high and low molecular weight polydiorganosiloxanes.

Suitable functional and nonfunctional MQ organopolysiloxane resins are commercially available from sources such as General Electric Co., Silicone Resins Division, Waterford, NY; PCR, Inc., Gainesville, FL; and Rhone-Poulenc, Latex and Specialty Polymers, Rock Hill, SC. Examples are disclosed in U.S. Pat. No. 5,082,706 (Tangney). Such resins are generally supplied in organic solvent and may be employed in the adhesives of the present invention as received. Typically, the amount of an MQ resin needed to achieve desired levels of release and peel forces will depend on the total amount of the high and low molecular weight polydiorganosiloxanes. The amounts of each of the components of the adhesives of the present invention are preferably chosen to provide the desired levels of peel and release forces described above. Preferably, at least about 50 weight parts MQ resin and no greater than about 70 weight parts MQ resin is used to achieve the desired level of release force, when the total weight parts (i.e., parts by weight) of MQ resin plus polydiorganosiloxanes (both high and low molecular weights) equals 100 parts.

Suitable organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule are commercially available from sources such as Dow Corning,

Midland, MI and General Electric Silicones, Waterford, NY. Examples are disclosed in U.S. Pat. No. 5,082,706 (Tangney).

Such silicone adhesives are prepared by addition-cure chemistry and typically involve the use of a platinum or other Group VIII B (i.e., Groups 8, 9, and 10) metal catalysts, typically, hydrosilation catalysts, to effect the curing of the silicone adhesive. Reported advantages of addition-cured silicone adhesives include reduced viscosity as compared to silicone adhesives prepared via condensation chemistry, higher solids content, stable viscosity with respect to time, and lower temperature cure. Methods of preparation are disclosed in U.S. Pat. No. 5,082,706 (Tangney).

The adhesive composition may include other additives to adjust for desired properties. For example, pigment may be added as colorant; conductive compounds may be added to make an adhesive surface electrically conductive or antistatic; antioxidants and bacteriostatic agents may be added; light absorbers may be added to block certain wavelengths from passing through the article; or inhibitors may be added to extend adhesive pot life, thus avoiding premature gelation of the adhesive coating solution. Examples of such additives are commercially available from various sources and are disclosed in U.S. Pat. No. 5,082,706 (Tangney), as are desired amounts.

The adhesive composition can be applied to appropriate release liners by a wide range of processes, including, solution coating, solution spraying, etc., to make adhesive/release liner laminates, preferably at a coating weight of about 0.2 grams/154.2 cm<sup>2</sup> to about 2.4 grams/154.2 cm<sup>2</sup>. Typically, it is applied to a thermally resistant substrate, such as polyethylene terephthalate coated with a fluorosilicone release material (such as that disclosed in U.S. Pat. No. 5,082,706 and commercially available from Rexam Release, Bedford Park, IL) to form an adhesive/release liner laminate. The adhesive transfer tape is then laminated to a desired substrate, such as biaxially oriented polyethylene or high density polyethylene, to form an adhesive tape, particularly a cover tape for

an analytical receptacle. For evaluation of the release force of adhesives of the present invention, a release liner that releases Dow Corning 7657 silicone adhesive with a release force of less than about 10 N/dm is desired under the conditions described herein.

5                   Conventional cover tapes for microtiter plates include an adhesive layer and a backing such as aluminum (Al) foil or polyethylene terephthalate (PET). Aluminum foil backings are less desirable because they are not transparent. PET tape backings have high mechanical strength and resist puncture by all but the hardest, sharpest needles. A plastic pipette tip, for  
10                   example, requires high force to break through a very thin (approximately 1 mil or 25  $\mu\text{m}$ ) PET backing.

Suitable backings for use in the cover tapes of the present invention allow for puncture by needles or plastic sampling pipette tips, for example. Such puncture sites may or may not reclose (i.e., reseal).

15                   Alternatively, suitable backings that resist puncture can also be used. Preferably, the backing will puncture without splitting. The backings can be transparent, translucent, or opaque. Preferably, the backing is transparent. Transparency facilitates chemical analysis conducted by any one of several methods of photometric analysis including, for example, ultraviolet, visible, and  
20                   fluorometric analysis.

The backing can include a wide range of substrate materials, examples being polymer films such as polyethylene, polyethylene terephthalate (PET), biaxially oriented polypropylene (BOPP), and metallocene-polymerized poly(alpha-olefin) copolymers. These backing materials are generally resistant  
25                   to solvents commonly used in bioanalytical applications, as discussed above with respect to the adhesives. They can resist puncture or not, although if they are punctured, the puncture site does not reclose. Backings that allow for reclosure of the puncture site are also possible.

The analytical receptacles to which the cover tapes can be applied include a wide variety of articles. Preferably, the analytical receptacles include at least one surface having one or more reservoirs therein. For example, a suitable analytical receptacle to which a cover tape of the present invention can  
5 be applied includes a microtiter plate, which is typically a plastic plate containing a number of small flat-bottomed wells arranged in rows. Another example is a tape that includes a substrate coated with a gel having a plurality of separate adjacent tracks thereon, as disclosed in U.S. Pat. No. 3,551,295 (Dyer).

Other analytical receptacles include microfluidic devices that  
10 include a substrate and one or more channels therein. Such a structure, which includes a body structure and at least one microscale channel disposed therein, is disclosed in U.S. Pat. No. 5,842,787 (Kopf-Sill et al.). Yet another such structure, which has a groove recessed in a flat substrate and defines a microfluidic channel system, is disclosed in U.S. Pat. No. 5,443,890 (Ohman).  
15 Yet another such structure, which includes a substrate with microstructures fabricated therein, is disclosed in U.S. Pat. No. 5,804,022 (Kaltenbach et al.).

Another type of analytical receptacle includes a substantially continuous polymeric strip formed to have wall portions defining a series of identical reservoirs at predetermined, preferably, uniformly spaced, intervals  
20 along its length, which reservoirs can have a variety of shapes. For example, the reservoirs may comprise rectangular or generally "I" or "T" shapes in the plane of the strip, and may have flat or rounded bottoms as desired. Such receptacles are disclosed, for example, in U.S. Pat. No. 4,883,642 (Bisconte). Others are disclosed in U.S. Pat. No. 5,729,963 (Bird), which are designed for carrying  
25 electrical parts, but can be modified for use as analytical receptacles.

These analytical receptacles can be formed from a variety of materials, including, polyethylene, polystyrene, polypropylene, polycarbonate, which can be carbon-black or  $\text{TiO}_2$  filled, transparent, translucent, or opaque.

### Experimental

Objects and advantages of this invention are further illustrated by the following examples, but the particular materials and amounts thereof recited in these examples, as well as other conditions and details, should not be construed to unduly limit this invention.

### Test Methods

10                   **Peel Force Test:** An 1-inch (2.54 cm) wide by 6-inch (15.24 cm) strip of each test adhesive tape sample was placed on a 20 mil (0.05 cm) thick polypropylene plate. A 5-pound (2.27-kg) roller was then used to apply the tape to the plate assembly to insure uniform contact. Subsequently, an Imass Slip/Peel Tester model SP-102B-3M90 (Instrumentors Inc., Strongsville, OH) was used to measure a 180° peel force between the silicone adhesive and the polypropylene plate at a plate speed of 12 inches/minute (30.5 cm/minute), according to ASTM D3330-D3330M-96. An average peel force per inch of plate travel was registered on the tester. The test was repeated three times and average value reported in Newtons per decimeter (N/dm).

20                   **Release Force Test:** A tape laminate, 1-inch (2.54 cm) wide by 6-inch (15.24 cm) long consisting of a tape backing, a layer of silicone adhesive, and a fluorosilicone coated release liner (CLPET – 6J/000 available from Rexam Release Corporation, Bedford Park, IL) was adhered to the clean glass base plate of an Imass tester (Model SP-102B-3M90) with SCOTCH tape #411 (3M Company, St. Paul, MN). The 180° release force between release liner and silicone adhesive was measured at 30.5 cm/minute speed according to ASTM D3330-D3330M-9 by pulling the backing/adhesive laminate from the release liner. The average release force per inch of plate travel was registered on the

tester and recorded. The experiment was repeated three times and average value reported in N/dm.

**Cross Contamination Test:** In a polystyrene 96-well microplate (available from Nalge International Corp, Naperville, IL) alternating wells were filled with approximately 50  $\mu$ l of a red colorant solution (MERTHIOLATE, supplied by Eli Lilly, approximately 1:50 dilution in water) and the openings of the wells of the microplate were covered by the sample adhesive cover tapes. The covered plate was subsequently inverted and shaken several times. The wells in the plate were then visually observed to determine if the indicator solution had migrated to an adjacent well.

**Solvent Resistance Test:** Sample adhesive tapes were adhered to an aluminum plate with 6 wells, each well having a dimension of 0.6 cm diameter and 0.6 cm depth. Prior to application of the cover tape, DMSO (50  $\mu$ l) was filled in each well and allowed to dwell for 24 hours in the tape-covered wells. The tapes were subsequently inspected visually for evidence of swelling or dissolution.

**Extractables Test:** Samples (4 cm x 5 cm) of each adhesive cover tape were soaked in 5 ml of water or dimethyl sulfoxide (DMSO) for 24 hours. The sample adhesive tapes were also exposed to vapor phase contact with the solvents in the wells of the sample adhesive tape-covered aluminum plate described above for 7 days. The extracts were examined by gas chromatography/mass spectroscopy (GC/MS) using a Finnigan "Magnum" GC/ion trap mass spectrometer (available from Thermoquest Corporation., San Jose, CA) equipped with a model ZB-5 column (30 meters in length, 0.25 mm inner diameter, 0.1  $\mu$ m film (available from Phenomenex Torrence, CA), a 4-ml Atas Optic 2 injector (available from Atas, Cambridge Cambridgeshire, United Kingdom), and a Finnegan scanning electron impact detector available from Thermoquest Corporation, San Jose, CA (electron impact scan range from 31 Daltons to 550 Daltons. The Atas injector was operated in a cold split, multi-

capillary liner mode with a helium carrier gas flow rate of about 1 ml/minute.

The injection temperature was programmed at 30°C/second to 350°C, the oven temperature was programmed to start from 50°C incrementally ramping at

20°C/minute to a final temperature of 320°C which was held for 2.5 minutes at

- 5 the end of the run and the transfer line temperature was set at 300°C. The helium carrier gas pressure was programmed at 10 pounds per square inch (psi) initially to 20 psi after 16 minutes.

- Residual Adhesive on Probe Puncture Test:** Sample tapes of the noted compositions were adhered to a clear polystyrene 96-well nontreated microplate (No. 3367 available from Corning Inc., Corning, NY). Each cover  
10 tape was punctured five consecutive times at different locations with either a 22 gauge needle or a 10 µl plastic tip (available from Eppendorf Corp., Germany). Subsequent to the puncture of each tape the barrel of the needles and the plastic tips were visually inspected (10x magnification) for evidence of adhesive  
15 residue adhering to these puncturing devices.

- Rate of Sample Evaporation Test:** A PCR (polymerase chain reaction) 96-well polypropylene Microamp Optical Plate, model N-8010560 (available from Perkin Elmer Biosystems Co., Norwalk, CT) was filled with 50 µl of solvent in each well. A test sample of an adhesive cover tape was then  
20 adhered to the Microamp optical plate covering the well openings. Weight loss due to evaporation of the water was monitored gravimetrically as a function of time at room temperature (approximately 24°C) over a period of 24 hours, to detect any change.

25

### Examples 1-25

#### Materials

- Dow Corning 7657 (available from Dow Corning Corporation,  
30 Midland, MI) silicone adhesive containing 56.5 parts silicone solids (44 wt %



vinyl dimethylsiloxane terminated polydimethylsiloxane with molecular weight approximately 500,000 and 56 wt % nonreactive MQ tackifying resin) with xylene as the diluent. Additional amounts of the same nonreactive MQ tackifying resin were added by the manufacturer to the Dow Corning 7657 adhesive to provide adhesive solutions 7657-2, 7657-4, 7657-6, and 7657-8 containing 58, 60, 62, and 64 wt % MQ respectively. Toluene (available from Worum Chemical Company, St. Paul, MN) was added to each formulation to provide the adhesive at 40 wt % solids content for ease of coating.

Dow Corning (Dow Corning Corporation, Midland, MI) SYL-OFF 7615 release modifier (designated as 7615) containing approximately 40 wt % dimethylvinylated and trimethylated silica; 57 wt % dimethylsiloxane, dimethylvinyl terminated with a degree of polymerization of 25; 1 wt % tetra(trimethylsiloxy) silane; 1 wt % of a Dow Corning proprietary ester; and a platinum-containing catalyst.

Dow Corning SYL-OFF 7678 crosslinker (designated as 7678) containing dimethylsiloxane methylhydrogensiloxane copolymer.

Dow Corning SYL-OFF 4000 catalyst (designated as 4000) containing dimethylvinyl terminated polydimethylsiloxane, tetramethyldivinyl disiloxane, and a platinum siloxane complex.

20

#### Formulations

Adhesive Composition A: 250 parts of Dow Corning 7657 silicone base adhesive at 40% solids in toluene/xylene, and 1 part of SYL-OFF 4000 catalyst.

25

Adhesive Composition B: 250 parts of Dow Corning 7657-2 silicone base adhesive at 40% solids in toluene/xylene, and 1 part of SYL-OFF 4000 catalyst.

Adhesive Composition C: 250 parts of Dow Corning 7657-4 silicone base adhesive at 40% solids in toluene/xylene, and 1 part of SYL-OFF 4000 catalyst.

Adhesive Composition D: 250 parts of Dow Corning 7657-6  
5 silicone base adhesive at 40% solids in toluene/xylene, and 1 part of SYL-OFF 4000 catalyst.

Adhesive Composition E: 250 parts of Dow Corning 7657-8 silicone base adhesive at 40% solids in toluene/xylene, and 1 part of SYL-OFF 4000 catalyst.

10 Modifier 7615: 93 parts of SYL-OFF 7615 release modifier and 7 parts of SYL-OFF 7678 crosslinker.

The silicone adhesives were prepared according to the formulations listed above in the proportions disclosed in Tables 1-5. Adhesive  
15 Compositions A-E were prepared by combining the above-listed components and mixing two to four hours on a roller at room temperature. Modifier 7615 was added to the Adhesive Compositions A-E and mixed on a roller at room temperature for an additional two to four hours to obtain homogeneous adhesive solutions for coating.

20 The resulting adhesive solution was applied on a release liner (CLPET-6J/000 transfer liner from Rexam Release Corp., Beford Park, IL) using a knife coater at 6-7 mils orifice, dried and cured by passing through a three-zone oven, at a rate of 3 feet/minute (0.914 meters/minute). The oven zone temperatures and residence times were 71 °C for 3 minutes, 82 °C for 3  
25 minutes, and 82 °C for 6 minutes, respectively. A balance was then used to confirm an adhesive coating weight of approximately 0.768-0.896 grams per 154.8 cm square.

The silicone adhesive/release liner laminate was then laminated to an embossed tape backing, 0.01 cm thick, corona-treated ethylene/propylene

copolymer (PP-PE) film (BPI Code #26379-3, Bloomer Plastics Inc., Bloomer, WI) by passing the adhesive/release liner laminate and embossed tape backing through a nip roll.

The peel force test and release force test were measured on each of the prepared samples and reported in Tables 1-5. The results suggest that there is little effect on the peel forces of the silicone tapes when 0-20 parts of silicone modifier were added to the silicone adhesive. Surprisingly, the results show that addition of silicone modifier serves to decrease release force without adversely affecting peel adhesion.

10

Table 1

Adhesive Composition A with 0, 5, 10, 15, and 20 parts of Modifier 7615			
Example	Modifier 7615	Peel Force (N/dm)	Release Force (N/dm)
1	0 part	24.6	7.1
2	5 parts	22.0	6.7
3	10 parts	21.2	4.4
4	15 parts	21.5	2.1
5	20 parts	22.5	1.5

15

Table 2

Adhesive Composition B with 0, 5, 10, 15, and 20 parts of Modifier 7615			
Example	Modifier 7615	Peel Force (N/dm)	Release Force (N/dm)
6	0 part	21.5	4.5
7	5 parts	23.8	2.4
8	10 parts	24.5	1.0
9	15 parts	23.1	1.2
10	20 parts	25.1	1.0

5

Table 3

Adhesive Composition C with 0, 5, 10, 15, and 20 parts of Modifier 7615			
Example	Modifier 7615	Peel Force (N/dm)	Release Force (N/dm)
11	0 part	25.2	2.8
12	5 parts	23.5	2.9
13	10 parts	27.8	0.4
14	15 parts	27.4	0.2
15	20 parts	28.2	0.2

Table 4

Adhesive Composition D with 0, 5, 10, 15, and 20 parts of Modifier 7615			
Example	Modifier 7615	Peel Force (N/dm)	Release Force (N/dm)
16	0 part	20.9	0.4
17	5 parts	22.3	0.3
18	10 parts	29.8	0.2
19	15 parts	30.3	0.2
20	20 parts	26.7	0.2

5

Table 5

Adhesive Composition E with 0, 5, 10, 15, and 20 parts of Modifier 7615			
Example	Modifier 7615	Peel Force (N/dm)	Release Force (N/dm)
21	0 part	4.8	0.08
22	5 parts	8.7	0.09
23	10 parts	4.2	0.03
24	15 parts	7.0	0.04
25	20 parts	8.5	0.05

### Examples 26-47 and Comparative Examples C1-C5

#### 5 Materials

Dow Corning 7657 silicone adhesive diluted to 40 wt % solids with toluene.

Vinyl Fluid A: a vinyl dimethylsiloxane terminated polydimethylsiloxane fluid with degree of polymerization of 24.

10 Vinyl Fluid B: a vinyl dimethylsiloxane terminated polydimethylsiloxane fluid with degree of polymerization of 67.

Vinyl Fluid C: a vinyl dimethylsiloxane terminated polydimethylsiloxane fluid with degree of polymerization of 101.

15 Vinyl Fluid D: a vinyl dimethylsiloxane terminated polydimethylsiloxane fluid with degree of polymerization of 167.

Vinyl Fluid E: a vinyl dimethylsiloxane terminated polydimethylsiloxane fluid with degree of polymerization of 245.

Vinyl Fluid F: a vinyl dimethylsiloxane terminated polydimethylsiloxane fluid with degree of polymerization of 459.

20 MQ resin solution: 63.4% nonreactive MQ resin (used in Dow Corning 7657 silicone adhesive) in xylene, provided by Dow Corning.

2EHHM: 2-ethylhexylhydrogen maleate was prepared by reacting one mole of maleic anhydride with one mole of 2-ethyl-1-hexanol.

### Formulations

Master batches of low molecular weight vinyl-substituted polydiorganosiloxanes ("vinyl-fluid" having varying degrees of polymerization) were prepared according to the following formulations.

5

Master Batch	Vinyl Fluid	Vinyl Fluid Amount (g)	MQ resin solution (g)	SYL-OFF 7678 crosslinker (g)	2EHHM (g)
A	A	21.0	46.4	2.1	0.17
B	B	19.1	39.8	0.72	0.15
C	C	19.3	39.8	0.49	0.15
D	D	19.5	39.8	0.30	0.15
E	E	19.6	39.8	0.21	0.15
F	F	19.7	39.8	0.11	0.15

For each of the following examples, the proper amount of each Master Batch as indicated in Tables 6-11 was mixed with 50 grams of the 40% solids Dow Corning 7657 and 0.2 gm of SYL-OFF 4000. A tumbling roller was used for 2-4 hours to insure uniform mixing prior to coating.

The resulting adhesive solutions were applied on a release liner (CLPET-6J/000 transfer liner from Rexam Release, Bedford Park, IL) and coated, dried, and cured as in Examples 1-25, with the exception that oven zones 1, 2, and 3 were set at temperatures of 125°C, 149°C, and 149°C, respectively. The adhesive/release liner laminate was then laminated on a tape backing, BOPP (biaxially oriented polypropylene film) available from 3M Company, St. Paul, MN under the trade name SCOTCHPRO having a thickness of 31  $\mu$ m (1.2 mils). The BOPP tape backing was corona-treated to enhance bonding of the silicone

adhesive. The laminate of backing with adhesive and liner was constructed by passing the transfer tape and backing through a nip roll.

The peel force and release force of the tapes were measured utilizing the respective tests described above and reported in Tables 6-11. The release force for Example C1, which is the equivalent formulation to that of Example 1, has increased dramatically. This suggests that the fluorosilicone release liner (due to lot to lot variation) used for Tables 6-11 was less effective as compared with those in Tables 1-5. Nevertheless, the results in Examples 1-25 and Examples 26-47 confirm that adding low molecular weight silicone vinyl fluid (with or without reactive MQ resins) in the silicone adhesive formulations has a significant effect on lowering the release force of silicone adhesives from the release liner without adversely affecting peel adhesion. The data also suggest that a broad range of low molecular weight vinyl functional silicone fluids may be added in the silicone base adhesive with little effect on the peel forces of the silicone tapes.

Table 6  
Coating Formulation with Vinyl Fluid A (DP = 24)

Example	Master Batch	Master Batch Amount (g)	Amount of Vinyl Fluid A in Master Batch A (g)	Peel Force from PP (N/dm)	Release Force (N/dm)
C1	A	0	0.000	37.0	34.6
26	A	2.65	0.800	37.7	34.5
27	A	5.31	1.600	34.4	16.6
28	A	7.96	2.401	29.7	2.9
29	A	10.61	3.201	28.6	0.9
30	A	13.27	4.001	22.6	0.2
31	A	15.92	4.801	13.9	0.0



Table 7

5 Coating Formulation with Vinyl Fluid B (DP = 67)

Example	Master Batch	Master Batch Amount (g)	Amount of Vinyl Fluid B in Master Batch B (g)	Peel Force from PP (N/dm)	Release Force (N/dm)
32	B	7.96	2.543	28.9	16.6
33	B	10.61	3.391	25.9	11.4
34	B	13.27	4.239	22.5	8.5
35	B	15.92	5.087	21.2	6.7

10

Table 8

Coating Formulation with Vinyl Fluid C (DP = 101)

Example	Master Batch	Master Batch Amount (g)	Amount of Vinyl Fluid C in Master Batch C (g)	Peel Force from PP (N/dm)	Release Force (N/dm)
36	C	7.96	2.574	23.7	24.9
37	C	10.61	3.432	27.4	16.8
38	C	13.27	4.291	24.8	12.8
39	C	15.92	5.149	26.3	10.8

Table 9  
Coating Formulation with Vinyl Fluid D (DP = 167)

Example	Master Batch	Master Batch Amount (g)	Amount of Vinyl Fluid D in Master Batch D (g)	Peel Force from PP (N/dm)	Release Force (N/dm)
40	D	7.96	2.599	30.4	27.2
41	D	10.61	3.466	27.9	23.5
42	D	13.27	4.332	26.5	18.2
43	D	15.92	5.199	23.3	16.5

5

Table 10  
Coating Formulation with Vinyl Fluid E (DP = 245)

Example	Master Batch	Master Batch Amount (g)	Amount of Vinyl Fluid E in Master Batch E (g)	Peel Force from PP (N/dm)	Release Force (N/dm)
44	E	7.96	2.612	28.6	31.5
45	E	10.61	3.483	27.1	26.6
46	E	13.27	4.353	26.3	24.4
47	E	15.92	5.224	26.1	21.6

10

Table 11  
Coating Formulation with Vinyl Fluid F (DP = 459)

Example	Master Batch	Master Batch Amount (g)	Amount of Vinyl Fluid F in Master Batch F (g)	Peel Force from PP (N/dm)	Release Force (N/dm)
C2	F	7.96	2.625	31.8	37.0
C3	F	10.61	3.500	30.7	34.3
C4	F	13.27	4.375	28.8	35.3
C5	F	15.92	5.250	28.8	30.3

#### 5 Examples 48-49 and Comparatives C6-C11

The silicone adhesive composition of Example 13 on a release liner (CLPET-6J/000 transfer liner from Rexam Release Corporation, Bedford Park, IL) was laminated with the following backings.

Example 48 used an embossed high density polyethylene  
10 designated as PE (Product No. B100NA from Bloomer Plastics, Bloomer, WI). The embossed film thickness was 101.6  $\mu\text{m}$  (4 mils).

Example 49 used a biaxially-oriented polypropylene having a thickness of 30.5  $\mu\text{m}$  (1.2 mil) and designated as BOPP available by the trade designation SCOTCHPRO from 3M Company, St. Paul, MN.

15 In a polystyrene 96-well microplate (available from Nalge Nunc International Corp, Naperville, IL) alternating wells were filled with approximately 50  $\mu\text{l}$  of a red colorant solution (MERTHIOLATE, supplied by Eli Lilly, approximately 1:50 dilution in water) and the openings of the wells of the microplate were covered by the sample adhesive cover tapes of Examples 48  
20 and 49. The covered plate was subsequently inverted and shaken several times.

The wells in the plate were then visually observed that showed no indicator solution had migrated to an adjacent well.

Samples of the tapes of Examples 48 and 49 were applied over a 96-well polypropylene microplate (Cat. No. 3364 available from Corning Inc.,  
5 Corning , NY), with DMSO in the micro-wells, for 24 hours under ambient conditions. There was no noticeable change of adhesion of the cover tapes of the invention to the polypropylene plate. However, Comparative Example C6 consisting of a nitrile rubber adhesive tape labeled (Product Number SJ3101 available from Minnesota Mining and Manufacturing Co., St. Paul, MN) and  
10 Comparative Example C7 consisting of a PET backing adhesive tape (THINSEAL tape available from PGC Scientifics, Gaithersberg, MD) each exhibited total loss of adhesion when exposed to the same test conditions, as shown in Table 12.

These same four cover tapes were adhered to a clear polystyrene  
15 96-well nontreated microplate (No. 3367 available from Corning Inc., Corning, NY). Each cover tape was punctured five consecutive times at different locations with a 22 gauge needle. Subsequent to the puncture of each tape the barrel of the needles were visually inspected (10x magnification) for evidence of adhesive residue adhering to these puncturing devices. These results are shown  
20 in Table 12.

Table 12

## DMSO Resistance of Silicone Tapes and Comparative Tapes

Example	Tape Backing	Adhesion in DMSO (24 hours)	Residue 22 G Needle
48	HDPE	Ok*	No residue visible
49	BOPP	Ok*	No residue visible
C6	SJ 3101	Swollen, lost adhesion	No residue visible
C7	THINSEAL	Swollen, lost adhesion	No residue visible

\*no noticeable change of adhesion.

5

Table 13 reports the extraction data obtained in the Extractables Test utilizing the GC/MS conditions listed above with several common solvents utilized within a typical bioanalytical lab when preparing sample that would be introduced to a multi-well aluminum plate and covered. Samples of the tapes were placed in DMSO, water and 80/20 acetonitrile/water mixture for 24 hours. Any extractable material was analyzed with GC/MS. The results indicated that no material was extracted from any of these tapes.

Comparative 8 was Corning cover tape (product number 3095) commercially available from Corning Corp., Corning, NY. Comparative 9 was product number 62367 cover tape available from Zymark Corp., Hopkinton, MA. Comparative 10 was Costar product number 6569 cover tape available from Corning Costar Corp., Acton, MA. Comparative 11 was Ultra-Plate cover tape available from Sagian Corporation, Indianapolis, IN. Each of these cover tape samples were used as received. The results demonstrate a significant value of the present invention is the ability of cover tapes of the present invention to resist commonly used solvents in bioanalytical applications.

Table 13

Tape Extraction Data by GC/MS with several common solvents for 24 hours

Example	Tape/PSA	DMSO ( $\mu\text{g}/\text{cm}^2$ total extractants)	80/20 AN*/H <sub>2</sub> O ( $\mu\text{g}/\text{cm}^2$ total extractants)	Water ( $\mu\text{g}/\text{cm}^2$ total extractants)
49	Silicone	< 5	N.T.	0-1
Comp. 8	Corning 3095	~5,000**	~5,000**	N.T.
Comp. 9	Zymark P/N 62367	~5,000**	N.T.	N.T.
Comp. 10	Costar 6569	15	7	N.T.
Comp. 11	Ultra-Plate	~5,000**	N.T.	N.T.

N.T. = not tested.

5 \* AN=acetonitrile.

\*\*Indicates that sample fully dissolved in extractant and exceeded the measurable range of the instrument. Values were calculated by mass balance before and after extraction.

10 **Evaporation Rates of Example 42 and Comp. 12**

Table 14 compares the evaporation rate of water in 24 hours for cover tapes applied to a Perkin Elmer PCR 96-well plate. The tapes consisted of the silicone cover tape of Example 42 having a peel adhesion around 27 N/dm, and Comparative Example 12, CYCLE SEAL cover tape (by Robbins Scientific Corp., Sunnyvale, CA) having a peel adhesion less than 5 N/dm. The data show that the silicone tape of the present invention provides a superior seal against the plate well as compared to a commercial cover tape having low peel adhesion.

Table 14

Evaporation Rates of Water in 24 Hours on a Perkin Elmer PCR 96-Well Plates

Example	Samples	Evaporation/24 hr
42	BOPP with silicone PSA	~3%
Comp 12	Robbins (CYCLESEAL) 30 mils Thick, low peel	~25%

5

**Evaporation Rates of Example 50 and Comp. 13-15**

Example 50 utilized the adhesive of Example 42 and a 3-layer (A/B/A) coextruded film for the adhesive tape backing, where outerlayer A (thickness = 7 microns) was FINA polypropylene #3825 (available from FINA Oil & Chemical Co., Dallas, TX) and B is KRATON G1657 (available from Shell Chemical, Houston, TX) (thickness = 63 microns). The films were prepared on a coextrusion line using a Cloeren (Orange, Texas) ABBBC feedblock. The B Layer (elastic core) was split into three layers in the feedblock, recombined and sandwiched between the two skin layers to form the three-layer coextruded film. The A Layer (skin 1) was cast against a rubber nip roll. The C Layer (skin 2) was cast against a patterned steel chill roll. Extruder A (skin 1) was a 2.5-inch single screw (24:1 L/D) manufactured by David Standard Corporation (Pawcatuck, CT). Extruder B (elastic core) was a 2.5-inch single screw (32:1) manufactured by Extruders Inc. and Extruder C (skin 2) was a 1.5-inch single screw (24:1 L/D) manufactured by David Standard.

Comparative Examples 13 and 14 were commercially available adhesive tapes. Aluminum adhesive tape (Comp. 13, from Marsh Biomedical Products, Inc., Rochester, NY) and a PET adhesive tape (Comp. 14, trade name

THINSEAL from PGC Scientifics, Gaithersburg, MD) were used for comparison. Comparative 15 was an open well (without a cover tape).

After removing the release liner from the tapes of Example 50 and Comparatives 13 and 14, they were used as cover tapes to seal a 96-well  
5 polypropylene Microamp Optical Plate, model N-8010560 (available from Perkin Elmer Biosystems Co., Norwalk, CT) filled with 50  $\mu$ l of water in each well.

In a first experiment, the adhesive cover taped microplate of Example 50 was inverted with the adhesive in contact with the openings of the  
10 microwells. The tape of Example 50 was then pierced several times using an 18-gauge stainless steel needle of a hypodermic syringe to facilitate removal of water from selected micro-wells. After withdrawing the needle, and inverting the microplate, there was no visual evidence of leakage from any micro-well covered with the tape of Example 50. It should also be noted that after  
15 completing the penetration test, there was no evidence of adhesive residue on the surface of the probe used to pierce the cover tape of Example 50.

In a second experiment, the cover tapes of each of Examples 50 and Comparatives 13 and 14 were pierced with a 22-gauge needle at room conditions. Table 15 shows the evaporation rates of the pierced cover tapes of  
20 this second experiment applied to the surface of a 96-well polypropylene Microamp Optical Plate, model N-8010560 (available from Perkin Elmer Biosystems Co., Norwalk, CT) filled with representative solvents. The solvents covered by the tapes were acetonitrile/water (84:16 by wt), water, and DMSO. For Example 50, loss by evaporation was minimal and no leakage was detected  
25 after shaking the plate vigorously, as compared to Comparatives 13 and 14. The negative value for Example 50 with DMSO appears to be due to sorption of moisture by DMSO at room condition. Comparative 15 showed the evaporation rate of the solvent without a cover tape.



Table 15  
Effect of A Septum Tape Backing on the Evaporation Rates of Some  
Commonly Used Solvents

Example	Solvents	Evaporation/hr
50	Acetonitrile: Water (84:16 by wt).	0.12%
50	Water	0.02%
50	DMSO	-0.02%
Comp 13	Acetonitrile: Water (84:16 by wt).	0.75%
Comp 14	Acetonitrile: Water (84:16 by wt).	1.10%
Comp 15*	Acetonitrile: Water (84:16 by wt).	29%

\* No cover tape

5

#### **Peel Force of Cover Tapes from Nitrile Rubber**

Peel force of adhesive tapes from a nitrile rubber surface (type: N-DEX 60005 PFM powders free, Best Manufacturing Co., Menio, GA) were measured using the Peel Force Test described above, except a portion of a nitrile rubber glove was adhered to the polypropylene plate with SCOTCH tape #411 (3M Company, St. Paul, MN). The data is shown in Table 16 for the cover tapes of Examples 11-15 and Comparative 14. The silicone tapes in this invention have very low peel adhesion to the commonly used rubber gloves. Furthermore, the silicone tapes have very low tack when touched with fingers or rubber gloves.

15

Table 16  
Peel Adhesion of Tapes on Nitrile Rubber Glove Surfaces

5

Example	Peel Adhesion (N/dm)
Example 11	2.2
Example 12	1.7
Example 13	0
Example 14	0
Example 15	0
Comp. 14	19.0

10

The complete disclosures of the patents, patent documents, and publications cited herein are incorporated by reference in their entirety as if each were individually incorporated. Various modifications and alterations to this invention will become apparent to those skilled in the art without departing from the scope and spirit of this invention. It should be understood that this invention

15 is not intended to be unduly limited by the illustrative embodiments and examples set forth herein and that such examples and embodiments are presented by way of example only with the scope of the invention intended to be limited only by the claims set forth herein as follows.

20

WHAT IS CLAIMED IS:

1. An adhesive prepared from components comprising:
  - (a) a polydiorganosiloxane having the general formula  
5  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  and a number average molecular weight of at least 20,000, wherein each R is independently a monovalent hydrocarbon group, each  $R^1$  is independently an alkenyl group, and n is an integer;
  - (b) a polydiorganosiloxane having the general formula  
10  $R^1R_2SiO(R_2SiO)_m(R^1RSiO)_nSiR_2R^1$  and a number average molecular weight of less than 20,000, wherein each R and  $R^1$  is independently a monovalent hydrocarbon group, at least two  $R^1$  groups are alkenyl groups, and m and n are integers the sum of which provide an alkenyl equivalent weight of about 250 to about 10,000;
  - (c) an organopolysiloxane MQ resin which contains  $(R^2)_3SiO_{1/2}$  units and  
15  $SiO_2$  units in a molar ratio in the range of 0.6:1 to 1:1, wherein each  $R^2$  is independently selected from the group of alkyl groups, alkenyl groups, or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl groups;
  - (d) an organohydrogenpolysiloxane free of aliphatic unsaturation having  
20 an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in components (a) through (c); and
  - (e) a Group VIII B-containing catalyst in a quantity sufficient to provide  
25 0.1 to 1,000 weight parts Group VIII B metal for each one million weight parts of the combined quantity of components (a) through (d).
2. The adhesive of claim 1 wherein the organopolysiloxane MQ resin includes both nonfunctional and functional MQ resins.

3. The adhesive of claim 2 wherein the functional MQ resin includes alkenyl groups.
- 5 4. The adhesive of claim 1 when disposed on a fluorosilicone-coated polyethylene terephthalate release liner and a propylene/ethylene copolymer backing at a coating weight of 0.8 grams/154.8 cm<sup>2</sup> to form a laminate, and when adhered to a glass plate, displays a 180° release force of no greater than about 20 N/dm when measured at 30.5 cm/minute and  
10 room temperature.
5. The adhesive of claim 4 which displays a release force of no greater than about 15 N/dm.
- 15 6. The adhesive of claim 5 which displays a release force of no greater than about 10 N/dm.
7. The adhesive of claim 6 which displays a release force of no greater than about 5 N/dm.  
20
8. The adhesive of claim 1 when disposed on a propylene/ethylene copolymer backing at a coating weight of 0.8 grams/154.8 cm<sup>2</sup> and adhered to a polypropylene plate displays a 180° peel force of at least about 5 N/dm when measured at 30.5 cm/minute and room temperature.  
25
9. The adhesive of claim 1 which is a pressure sensitive adhesive.
10. An adhesive article comprising a substrate having disposed on at least one major surface the silicone-based adhesive of claim 1.

11. The adhesive article of claim 10 wherein the organopolysiloxane MQ resin includes both nonfunctional and functional MQ resins
- 5 12. The adhesive article of claim 10 further comprising a release liner disposed on the adhesive.
13. The adhesive article of claim 10 wherein the adhesive when disposed on a fluorosilicone-coated polyethylene terephthalate release liner and a  
10 propylene/ethylene copolymer backing at a coating weight of 0.8 grams/154.8 cm<sup>2</sup> to form a laminate, and when adhered to a glass plate, displays a 180° release force of no greater than about 20 N/dm when measured at 30.5 cm/minute and room temperature.
- 15 14. The adhesive article of claim 13 wherein the adhesive displays a release force of no greater than about 5 N/dm.
15. The adhesive article of claim 10 wherein the adhesive when disposed on a propylene/ethylene copolymer backing at a coating weight of 0.8  
20 grams/154.8 cm<sup>2</sup> and adhered to a polypropylene plate displays a 180° peel force of at least about 5 N/dm when measured at 30.5 cm/minute and room temperature.
16. The adhesive article of claim 10 wherein the backing comprises a  
25 puncturable material.
17. The adhesive article of claim 10 wherein the adhesive is a pressure sensitive adhesive.

18. An analytical receptacle comprising a surface and a cover tape adhered to the surface; wherein the cover tape comprises a backing and the adhesive of claim 1 disposed on at least one major surface of the backing and in contact with the receptacle surface.
- 5
19. The analytical receptacle of claim 18 further comprising one or more reservoirs in the form of a well or channel.
20. The analytical receptacle of claim 18 wherein the analytical receptacle comprises a substantially continuous tape.
- 10
21. The analytical receptacle of claim 18 wherein the adhesive is a pressure sensitive adhesive.
- 15
22. The analytical receptacle of claim 18 wherein the adhesive when disposed on a fluorosilicone-coated polyethylene terephthalate release liner and a propylene/ethylene copolymer backing at a coating weight of 0.8 grams/154.8 cm<sup>2</sup> to form a laminate, and when adhered to a glass plate, displays a 180° release force of no greater than about 20 N/dm when measured at 30.5 cm/minute and room temperature.
- 20
23. The analytical receptacle of claim 22 wherein the adhesive displays a release force of no greater than about 5 N/dm.
- 25
24. The analytical receptacle of claim 18 wherein the adhesive when disposed on a propylene/ethylene copolymer backing at a coating weight of 0.8 grams/154.8 cm<sup>2</sup> and adhered to a polypropylene plate displays a 180° peel force of at least about 5 N/dm when measured at 30.5 cm/minute and room temperature.

25. The analytical receptacle of claim 18 further comprising one or more reservoirs including a liquid therein during use.
- 5 26. The analytical receptacle of claim 25 wherein the liquid comprises dimethyl sulfoxide, water, acetonitrile/water, methanol, ethanol, or mixtures thereof.
27. The analytical receptacle of claim 18 comprising a microtiter plate.
- 10 28. The analytical receptacle of claim 18 comprising a microfluidic device comprising a substrate and one or more channels therein.
29. The analytical receptacle of claim 18 comprising a substantially  
15 continuous polymeric strip comprising a plurality of reservoirs at predetermined intervals along its length.
30. The analytical receptacle of claim 29 wherein the reservoirs are uniformly spaced.

31. An analytical receptacle comprising a surface comprising polypropylene, polystyrene, or combination thereof, and a cover tape adhered to the surface; wherein the cover tape comprises a backing and an adhesive disposed on at least one major surface of the backing and in contact with the receptacle surface, wherein the adhesive is prepared from components comprising:
- 5
- (a) a polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  wherein each R is independently a monovalent hydrocarbon group, each  $R^1$  is independently an alkenyl group and n is an integer;
- 10
- (b) an organopolysiloxane MQ resin which contains  $(R^2)_3SiO_{1/2}$  units and  $SiO_2$  units in a molar ratio in the range of 0.6:1 to 1:1, wherein each  $R^2$  is independently selected from the group of alkyl groups, alkenyl groups, or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl groups;
- 15
- (c) an organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in component (a) and component (b) if present; and
- 20
- (d) a Group VIIIB-containing catalyst in a quantity sufficient to provide 0.1 to 1,000 weight parts Group VIIIB metal for each one million weight parts of the combined quantity of components (a) through (c).
- 25
32. An analytical receptacle comprising a surface and a cover tape adhered to the surface; wherein the cover tape comprises a backing and an adhesive disposed on at least one major surface of the backing and in contact with



the receptacle surface, wherein the adhesive is prepared from components comprising:

- (e) a polydiorganosiloxane having the general formula  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  wherein each R is independently a monovalent hydrocarbon group, each  $R^1$  is independently an alkenyl group and n is an integer;
- (f) an organopolysiloxane MQ resin which contains  $(R^2)_3SiO_{1/2}$  units and  $SiO_2$  units in a molar ratio in the range of 0.6:1 to 1:1, wherein each  $R^2$  is independently selected from the group of alkyl groups, alkenyl groups, or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl groups;
- (g) an organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in component (a) and component (b) if present; and
- (h) a Group VIIIB-containing catalyst in a quantity sufficient to provide 0.1 to 1,000 weight parts Group VIIIB metal for each one million weight parts of the combined quantity of components (a) through (c);
- wherein the adhesive when disposed on a fluorosilicone-coated polyethylene terephthalate release liner and a propylene/ethylene copolymer backing at a coating weight of 0.8 grams/154.8 cm<sup>2</sup> to form a laminate, and when adhered to a glass plate, displays a 180° release force of no greater than about 20 N/dm when measured at 30.5 cm/minute and room temperature.

33. A method of making an adhesive comprising:

preparing a composition comprising:

- (a) a polydiorganosiloxane having the general formula  
5  $R^1R_2SiO(R_2SiO)_nSiR_2R^1$  and a number average molecular weight of at least 20,000, wherein each R is independently a monovalent hydrocarbon group, each  $R^1$  is independently an alkenyl group, and n is an integer;
- (b) a polydiorganosiloxane having the general formula  
10  $R^1R_2SiO(R_2SiO)_m(R^1R_2SiO)_nSiR_2R^1$  and a number average molecular weight of less than 20,000, wherein each R and  $R^1$  is independently a monovalent hydrocarbon group, at least two  $R^1$  groups are alkenyl groups, and m and n are integers the sum of which provide an alkenyl equivalent weight of about 250 to about 10,000;
- 15 (c) an organopolysiloxane MQ resin which contains  $(R^2)_3SiO_{1/2}$  units and  $SiO_2$  units in a molar ratio in the range of 0.6:1 to 1:1, wherein each  $R^2$  is independently selected from the group of alkyl groups, alkenyl groups, or hydroxyl groups, wherein at least 95 mole percent of all  $R^2$  groups are methyl groups;
- 20 (d) an organohydrogenpolysiloxane free of aliphatic unsaturation having an average of at least 2 silicon-bonded hydrogen atoms in each molecule, in a quantity sufficient to provide from 1 to 40 silicon-bonded hydrogen atoms per alkenyl group in components (a) through (c); and
- 25 (e) a Group VIIIB-containing catalyst in a quantity sufficient to provide 0.1 to 1,000 weight parts Group VIIIB metal for each one million weight parts of the combined quantity of components (a) through (d); and
- thermally curing the composition.

34. A method of sealing an analytical receptacle comprising applying a cover tape comprising a backing and the adhesive of claim 1 disposed on at least one major surface thereof.

REPLACED BY  
ART 34 AMDT

batch process with rate limitation due to the loading and positioning of the assay tray. Possible improvement in the rate of sample analysis results from the use of a continuous strip of material having sample wells molded along its length. U.S. Pat. No. 4,883,642 (Bisconte) suggests such a strip or tape. The patent teaches a

5 continuous ribbon, which may be either smooth or suitably molded to incorporate a plurality of micro-wells. Fixed biological sample analysis uses smooth versions of the continuous ribbons while micro-well ribbons find use for analyzing living biological samples. Two tracks, positioned along opposite edges of the ribbon, provide addressable means for moving and positioning the

10 ribbon in a selected, precise location with adjustment accurate to 10 micrometers ( $\mu\text{m}$ ). The tracks may be coded using magnetic, optical, or computer methods, for example, which allow manipulation and positioning of the ribbon. A dosage syringe type of device, positioned using a step by step motor, distributes biological samples in the micro-wells.

15 This continuous multi-reservoir carrier is useful in the automated analysis of biological samples, such as histological sections. Protection of the samples, whether applied to a smooth ribbon or contained in micro-wells may use a self-adhesive film. The self-adhesive film covers the smooth film surface or seals the openings to the individual micro-wells. It may be permeable or

20 impermeable to air.

U.S. Pat. No. 5,721,136 (Finney et al.) teaches the use of a multilayer sheet having a silicone adhesive thereon for use on vessels for biochemical reactions. One layer provides strength and integrity for the film. The second layer is a thick, in the range of about 2 mils to about 40 mils ( $50\ \mu\text{m}$

25 to  $1016\ \mu\text{m}$ ), deformable material with a very low tack surface. The elastic nature of the second layer results in good seal when clamped down during thermal cycling. The rubbery materials also provide a very low level of adhesion. The peel force of the sheet from a polypropylene surface is reported to be in the range of  $0.11\ \text{N/dm}$  to  $0.5\ \text{N/dm}$  ( $0.1\ \text{oz/in}$  to  $4.5\ \text{oz/in}$ ). Although a

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 99/09945

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 C09J183/07 B65B9/04

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C09J B65B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 581 539 A (GEN ELECTRIC) 2 February 1994 (1994-02-02) claims 1,3,4,9 page 5, line 31 -page 6, line 9 ---	1-3
A	US 5 082 706 A (TANGNEY THOMAS J) 21 January 1992 (1992-01-21) cited in the application claim 1 ---	1
A	US 5 721 136 A (TITCOMB PAUL ET AL) 24 February 1998 (1998-02-24) cited in the application claims 1-14 ---	1
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

5 January 2000

Date of mailing of the international search report

18/01/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Depijper, R

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/09945

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 729 963 A (BIRD GERALD C) 24 March 1998 (1998-03-24) cited in the application claim 1	1
A	EP 0 506 372 A (GEN ELECTRIC) 30 September 1992 (1992-09-30) claim 1	1

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/09945

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0581539	A	02-02-1994	CA 2101708 A JP 6166861 A	31-01-1994 14-06-1994
US 5082706	A	21-01-1992	AT 86286 T CA 2002073 A EP 0370689 A IE 62700 B JP 2189383 A KR 141486 B	15-03-1993 23-05-1990 30-05-1990 22-02-1995 25-07-1990 15-06-1998
US 5721136	A	24-02-1998	NONE	
US 5729963	A	24-03-1998	US 5648136 A CN 1190524 A DE 69601802 D DE 69601802 T EP 0838137 A JP 11509163 T WO 9703545 A	15-07-1997 12-08-1998 22-04-1999 04-11-1999 29-04-1998 17-08-1999 30-01-1997
EP 0506372	A	30-09-1992	US 5466532 A CA 2061973 A DE 69206457 D DE 69206457 T JP 5098240 A	14-11-1995 27-09-1992 18-01-1996 11-07-1996 20-04-1993